

TPE Corner Protector - 80mm x 80mm Datasheet

Product Code: RC4719

Technical Specification

Property	Test Method	Value
Hardness (Shore A)	ASTM D2240	67°
Density	ASTM D792	1.2kg/m ³
Tensile Strength	ASTM D412	7.0 MPa
Elongation at Break	ASTM D412	750%
Compression Set (22 hours, 23°C)	ASTM D395	15%
Compression Set (22 hours, 70°C)	ASTM D395	29%
Compression Set (22 hours, 100°C)	ASTM D395	54%
Reflexometric Fogging (3 hours, 100°C)	DIN 75201 A	96%
Gravimetric Fogging (16 hours, 100°C)	DIN 75201 B	10.65 MG
Operating Temperature	-	-40°C to +90°C



The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. RubberSmart cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.